

TEST REPORT

Client : AusProof (Pty) Ltd.
 : 6 Shona Avenue, Gladstone,
 : Queensland, Australia.

Distributors : AusProof (Pty) Ltd, KonNx Inc, KonNx Electrica, KonNx Africa, JoynX, KableX

Product : COMPOUD 78 ELECTRO INSULATING RESIN (HALOGEN FREE)

Date of Test : 22 October 2021

Document Identifier Number (DIN) : 944

SUMMARY OF RESULTS

Insulation properties tests have been carried out in accordance with the following standards.

Insulation property	Standard	Value	Comment	Result
Water absorption	ISO 62 ATSM D-570	< 0.5 % < 0.5 %	Test for 24 h at 23 °C	Complies
Electric strength	IEC 60243	> 8 kV/mm at 25 °C > 4 kV/mm at 100 °C	After conditioning	Complies
Surface resistance	IEC 60093 DIN IEC 93/167*	> 10 ⁹ Ω > 10 ⁹ Ω	—	Complies
Volume resistivity	IEC 60093 DIN IEC 93/167*	> 10 ⁹ Ω/cm > 10 ⁹ Ω/cm	25 °C 25 °C	Complies
CTI	IEC 60112	> 400	—	Complies
* DIN IEC 93/167 refers to the DIN equivalents of IEC 60093 and IEC 60167.				